



## E-1075 High Solids Fast Dry Chevy White Acrylic Enamel

### Description:

A Direct to Metal (DTM), high gloss, corrosion resistant enamel, for use on properly prepared steel and other metal surfaces. E-1075 offers rapid cure for handling after application, and can be applied over most primers and finish

### Product Information:

**Color:** White

**Weight Per Gallon:** 11.15 ± 0.30

**Solids By Weight:** 70.1 ± 2.0 %

**Solids by Volume:** 52.6 ± 2.0 %

**VOC:** < 3.50 Lb/Gal

**VOC Note:** < 420 grams per liter

**Gloss:** 90+ / 60 ° meter

**Viscosity:** 15-20" #3 Zahn

**pH Level:** N/A

**Pot Life:** N/A

### Recommended Application:

E-1075 exhibits excellent flow and leveling characteristics when using either conventional or airless spray systems. Surface of substrate must be clean, and free of excess oil, dirt, water or other contaminants, per SSPC-SP1.

### Clean Up Solvent(s):

Xylene

**Date:** 11/10/09

**Supersedes:** 12/16/08

### Reduction Rate/Mix Ratio:

Reduce 4:1 with an exempt solvent (acetone or TBA) if necessary.

### Curing Schedule: 77° F, 50% R. H. (Air Dry)

**Air Dry, Tack Free:** 45-60 minutes

**Dry Through:** 4-6 hours

**Bake, Flash Time:** N/A

**Bake Temp:** N/A

**Dwell Time:** N/A

**PMT:** N/A

**Theoretical Coverage @ 1.0 Mil:** 840 sq. ft. / gallon

### Recommended Dry Film Thickness:

2-3 mils

### Performance:

**Adhesion:** Excellent

**Durability:** N/A

**Flexibility:** Passes 180° bend with no cracking or peeling.

**Hardness:** N/A

**Impact:** N/A

**MEK Rubs:** N/A

**Salt Spray:** N/A

**Other:**

A Certificate of Analysis establishes specifications as a customer product requirement, otherwise these specifications are representative guidelines and may be modified on particular batches. The information and specifications stated here are for material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use, either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.